



Technical Specification - Technische Spezifikationen - Spécifications techniques - Technische specificaties

Thickness - Gesamtdicke - Epaisseur - Dikte	EN ISO 24337	2.00 mm
Wearlayer - Nutzschrift - Couche d'usure - Slijtlaag	EN ISO 24340	0.30 mm
Wearlayer PUR coating - Schuts vor Schmutz PUR - Traitement polyurethane - PUR slijtlaag behandeling		Scratchmaster® top layer
Weight per sqm - Flächengewicht g/m² - Poids total g/m² - Totaal gewicht g/m²	EN ISO 23997	ca. 3550 g/m²
Classification - Eignungsklasse - Classe d'usage - Gebruiksklasse	EN ISO 10874	23 Domestic Heavy - 31 Commercial Moderate



Performance - Prestaties

Reaction to fire - Brandverhalten - Classement feu - Brandklasse	EN 13501-1	Bfl-S1
Slip resistance - Rutschfest - Glissance - Antislip	EN 13893	DS
Slip restraint (dynamic coefficient of friction) - Rutschhemmung - Résistance au glissement - Slipweerstand	DIN 51130	R10
Thermal resistance R value - Wärmedurchlasswiderstand R - Résistance thermique R - Wamtedoorlaatweerstand R	EN 12664	0.027 (m².K)/W
Underfloor heating - Bodenheizung - Chauffage par le sol - Vloerverwarming	EN ISO 12524	Yes, max. 27°C
Electrostatic performance - Antistatik - Accumulation de charges électrostatiques - Electrostatische propensiteit	EN 1815	< 2 kV
Residual indentation - Eindrückverhalten - Poinçonnement rémanent - Restindruk	EN ISO 24343-1	< 0.1 mm
Dimensional stability - Massänderung - Stabilité dimensionnelle - Dimensionele stabiliteit	EN ISO 23999	≤ 0.15%
Curling - Schüsselung - Incurvation - Krulling	EN ISO 23999	pass
Castor chair resistance - Stuhlrollenfestigkeit - Résistance aux chaises à roulettes - Bestand tegen stoelwielen	EN ISO 4918	pass, Type W
Colour fastness - Farbechtheit - Solidité de la couleur - Kleurechtheid	EN ISO 105-B02	> 6
Impact sound insulation - Trittschallverbesserungsmaß - Efficacité acoustique - Kontaktgeluidisolatie	EN ISO 717-2	3dB (ΔLw)
Chemical / Stain resistance - Fleckenbeständigkeit - Résistance aux taches - Vlekbestendigheid	EN ISO 26987	pass
Abrasion resistance - Verschleißfestigkeit - Résistance à l'abrasion - Slijtvastheid	EN ISO 660-1	class T
Indoor AIR quality - French VOC regulation	ISO 16000	Greenguard GOLD - Floorscore - A+
Content of pentachlorophenol		PCP under detection limit
Formaldehyde emissions (28 days test)	EN ISO 717-1	NA HCHO (has not been added)
Phthalate free		Yes, biobased
CE marking	EN 14041:2011	

Packaging - Verpackung - Emballage - Verpakking

Size and packaging wood	EN ISO 24342	178x1219 mm (7"x48")	17 planks / carton = 3.69 m² (39.67 ft²) / carton
Size and packaging wood XL plank	EN ISO 24342	305x610 mm (12"x24")	20 planks / carton = 3.72 m² (40 ft²) / carton
Size and packaging wood parquet	EN ISO 24342	102x406 mm (4"x16")	36 planks / carton = 1.49m² (16ft²)/carton

Warranty - Garantie

Warranty - Garantie	20 years
----------------------------	----------

The technical data is correct at the time of printing. v1 - 10/2020



CERTIFIED BY
SCS Global Services